

CAPPING CEMENT SPECIFICATION

Grade Name: K17000/M

Applications:

Basic grade with improved humidity for linear fluorescent lamps and standard incandescent lamps upto and including 100 watts with 1500 hours lamp life.

Physical appearance:

Powder appearance:	Fine off white powder
Paste appearance:	Smooth dark green coloured paste
Cured appearance:	Dark straw coloured expanded solid

Physical properties:

Solvent:	ethanol (94%)	
Powder:solvent ratio:	8.5	L/100Kg powder @ 23°C
Viscosity:	275 - 325 (+/- .5)	10ths/mm paste penetration @ 23°C
Powder density:	1.0 - 1.2	g/cm ³ (tapped)
Paste density:	2.1 - 2.2	g/cm ³
Average expansion:	80 - 90	%
Moisture resistance:	excellent	
Paste storage life:	6 weeks	Stored in sealed containers @ 21°C (Note - Higher temperatures <u>reduce</u> life)
Powder storage life:	12 months	

The above properties are given for guidance purposes only. Individual customer requirements should be assessed prior to the use of cement. Technical assistance and test methods are available on request.

Health and Safety data sheets are available upon request

The information contained on this specification sheet is given in good faith and does not constitute a warranty or guarantee for the customer. Customers are advised to ensure that all products are thoroughly tested to ensure suitability for the intended application.

Glassbond (NW) Ltd, West Side Industrial Estate,
Jackson Street, St Helens, Merseyside, WA9 3AT England
Tel: +44 (0)1744 730334
Fax: +44 (0)1744 451661 (General) +44 (0)1744 733588 (Sales)
Email: info@glassbond.co.uk Web: www.glassbond.co.uk

Directors: PJ Randell Managing Director, RJ Randell, DJ Randell (M.I.M)
Glassbond (NW) Ltd. Registered Office: West Side Industrial Estate.
Registered in England No. 1378679



3607

E561

Capping cement information

Powder storage conditions

Keep containers tightly closed, store in a cool dry place out of direct sunlight. At 21°C a shelf life of 12 months is expected and at 30 °C a shelf life of 6 months is possible. However, temperatures higher than 30 °C and/or high humidity will further reduce shelf life, resulting in poor paste formation and may cause the powder to form lumps.

Recommended cleaning solvent:

Ethanol, isopropanol

Recommended mixing sequence:

1. Place alcohol in mixing vessel
 2. Add half of powder
 3. Mix for 5 minutes*
 4. Add remainder of powder
 5. Mix for a further 15 minutes*
 6. Allow to stand for 1 hour before use
- *mixing times vary

Recommended mixing machines:

Hobart
Winkworth
Z Blade type
Bowers Molteni

Recommended quantity of paste by cap type*:

(for guidance only)

B22d	1.5 - 1.7 g
E27	1.6 - 1.8 g
B22d	1.2 - 1.4 g
E14	0.9 - 1.0 g
B15d	0.9 - 1.0 g
T8	0.8 - 1.2 g
T10	1.3 - 1.5 g
T12	1.6 - 2.0 g

Curing Parameters:

As cement curing is influenced by paste weight, curing temperature and time, precise figures cannot be given.
For guidance purposes:

2 grams of paste @200°C will cure in 35 - 40 seconds
2 grams of paste @160°C will cure in 150 - 160 seconds

Prolonged exposure of curing cement to temperatures above 250°C should be avoided

The above properties are given for guidance purposes only. Individual customer requirements should be assessed prior to the use of cement. Technical assistance and test methods are available on request.

Health and Safety data sheets are available upon request

The information contained on this specification sheet is given in good faith and does not constitute a warranty or guarantee for the customer. Customers are advised to ensure that all products are thoroughly tested to ensure suitability for the intended application.

Glassbond (NW) Ltd, West Side Industrial Estate,
Jackson Street, St Helens, Merseyside, WA9 3AT England
Tel: +44 (0)1744 730334
Fax: +44 (0)1744 451661 (General) +44 (0)1744 733588 (Sales)
Email: info@glassbond.co.uk Web: www.glassbond.co.uk

Directors: PJ Randell Managing Director, RJ Randell, DJ Randell (M.I.M)
Glassbond (NW) Ltd. Registered Office: West Side Industrial Estate.
Registered in England No. 1378679



3607

E561