

## CAPPING CEMENT SPECIFICATION

**Grade Name: K192**

**Applications:** Grade suitable for high wattage lamps, with a life of up to 12000 hours at 350°C.

**Physical appearance:**

Powder appearance: White powder  
Paste appearance: White coloured paste  
Cured appearance: White coloured expanded solid

**Physical properties:**

Solvent:	ethanol (94%)	
Powder:solvent ratio:	8.0	L/100Kg powder @ 23°C
Viscosity:	275 - 325 (+/- 5)	10ths/mm paste penetration @ 23°C
Powder density:	not specified	g/cm <sup>3</sup> (tapped)
Paste density:	1.9 - 2.1	g/cm <sup>3</sup>
Average expansion:	80 - 90	%
Moisture resistance:	good	
Paste storage life:	8 weeks	Stored in sealed containers @ 21°C (Note - Higher temperatures <u>reduce</u> life)
Powder storage life:	6 months	Stored in sealed containers @ 30 °C

**The above properties are given for guidance purposes only. Individual customer requirements should be assessed prior to the use of cement. Technical assistance and test methods are available on request.**

The information contained on this specification sheet is given in good faith and does not constitute a warranty or guarantee for the customer. Customers are advised to ensure that all products are thoroughly tested to ensure suitability for the intended application.

**Glassbond (NW) Ltd**, West Side Industrial Estate,  
Jackson Street, St Helens, Merseyside, WA9 3AT England  
Tel: +44 (0)1744 730334  
Fax: +44 (0)1744 451661 (General) +44 (0)1744 733588 (Sales)  
Email: [info@glassbond.co.uk](mailto:info@glassbond.co.uk) Web: [www.glassbond.co.uk](http://www.glassbond.co.uk)

Directors: PJ Randell Managing Director, RJ Randell, DJ Randell (M.I.M)  
Glassbond (NW) Ltd. Registered Office: West Side Industrial Estate.  
Registered in England No. 1378679



3607

E561

## **Capping cement information**

### **Powder Storage conditions**

Keep containers tightly closed, store in a cool dry place out of direct sunlight. At 21°C a shelf life of 12 months is expected and at 30 °C a shelf life of 6 months is possible. However, temperatures higher than 30 °C and/or high humidity will further reduce shelf life, resulting in poor paste formation and may cause the powder to form lumps.

### **Recommended cleaning solvent:**

Ethanol, isopropanol

### **Recommended mixing sequence:**

1. Place alcohol in mixing vessel
2. Add half of powder
3. Mix for 5 minutes (mixing times vary)
4. Add remainder of powder
5. Mix for a further 15 minutes (mixing times vary)
6. Allow to stand for 1 hour before use, to ensure full dissolution of the resins.

### **Recommended mixing machines:**

Hobart  
Winkworth  
Z Blade type  
Bowers Molteni

### **Recommended quantity of paste by cap type\*:** (for guidance only)

B22d	1.5 - 1.7 g
E27	1.6 - 1.8 g
B22d	1.2 - 1.4 g
E14	0.9 - 1.0 g
B15d	0.9 - 1.0 g

### **Curing Parameters:**

As cement curing is influenced by paste weight, curing temperature and time, precise figures cannot be given. For guidance purposes:

- 2 grams of paste @300°C will cure in 10 - 15 seconds
- 2 grams of paste @200°C will cure in 35 - 40 seconds
- 2 grams of paste @160°C will cure in 150 - 160 seconds

Prolonged exposure of curing cement to temperatures above 350°C should be avoided

**The above properties are given for guidance purposes only. Individual customer requirements should be assessed prior to the use of cement. Technical assistance and test methods are available on request.**

### **Health and Safety data sheets are available upon request**

The information contained on this specification sheet is given in good faith and does not constitute a warranty or guarantee for the customer. Customers are advised to ensure that all products are thoroughly tested to ensure suitability for the intended application.

Glassbond (NW) Ltd, West Side Industrial Estate,  
Jackson Street, St Helens, Merseyside, WA9 3AT England  
Tel: +44 (0)1744 730334  
Fax: +44 (0)1744 451661 (General) +44 (0)1744 733588 (Sales)  
Email: info@glassbond.co.uk Web: www.glassbond.co.uk

Directors: PJ Randell Managing Director, RJ Randell, DJ Randell (M.I.M)  
Glassbond (NW) Ltd. Registered Office: West Side Industrial Estate.  
Registered in England No. 1378679



3607

E561