

# C-Bond

by

**Glassbond**

## Technical Data Sheet

### L148 – Instant Adhesive

#### Characteristics

- ❑ Clear rubber-toughened
- ❑ Higher peel and shock resistance
- ❑ One-component adhesive, no need for hardeners
- ❑ Atmospheric moisture-activated cure
- ❑ Invisible bond line

#### Recommended For

Rubber	Ceramic
Metal	Leather
Plastics	Cardboard
Wood	Paper

#### Description

Glassbond Instant Adhesive L148 is a clear rubber-toughened, high viscosity cyanoacrylate adhesive.

#### **Physical properties**

Appearance	Clear
Specific gravity (at 25°C)	1.05 – 1.06
Viscosity	3500 – 6000 cP
Shelf life	6 months at 2-10°C in original unopened packaging

#### **Bonding speed**

	<b>Time (seconds)</b>
Steel	16 to 22
Aluminium	11 to 19
Rigid PVC	4 to 8
Nitrile Rubber	5 to 10

Tensile shear strength, cured for 24 hours at 20-25°C

**Physical properties were determined on specimens prepared under laboratory conditions. Actual field conditions may vary and yield different results; therefore, data are subject to reasonable deviation. Data should not be used for specification purposes.**

## **Application / Instructions**

PREPARATION – Bring the adhesive to room temperature prior to use and ensure the surfaces to be bonded are clean and free from dirt or grease. Cleaning can be carried out with standard grade solvents such as IMS or acetone. This adhesive uses residual surface moisture to cure so there is no requirement to dry the surfaces prior to use. The substrate that doesn't have adhesive applied to it can be prepared by carefully exhaling on it to create a humid environment.

APPLICATION - Use as thin a bond line as possible while ensuring complete coverage of the target area. Apply Glassbond Instant Adhesive L148 to one substrate and hold the parts together firmly by hand. If the substrates are able to be clamped together the tensile/torque strength can be improved. The thinner the bond line, the stronger the bond. Due to its thixotropic nature this adhesive won't run and should demonstrate a good ability to stay in place when applying. Avoid contact with natural fibres such as cotton and wool.

## **Setting / Curing**

When bonding glass to metal Glassbond Instant Adhesive L148 will form a hand-tight grip within seconds however other substrates may vary in bonding speed. Suitable pressure by hand should be applied when bonding. Full strength will be achieved after 24 hours at room temperature.

## **Cleaning**

Excess adhesive should be left to set before scraping or abrading away with an emery board.

## **Packaging**

This material is supplied in various types and sizes of containers. Please contact Glassbond's sales department for further details ([sales@glassbond.co.uk](mailto:sales@glassbond.co.uk)).

## **Shelf Life**

Glassbond Instant Adhesive L148 has a shelf life of 6 months when stored in unopened, tightly sealed containers in a dry location at 2°C to 10°C. Maximum storage temperature is 25°C. HDPE containers do not offer a complete barrier, store away from other chemicals and sources of humidity. Strong light exposure can discolour product. If there is doubt as to the quality of the material, consult Glassbond.

## **Caution**

Consult the Material Safety Data Sheets and container label caution statements for any hazards in handling this material.

## **Warranty**

We warrant that our goods will conform to the description contained in the order and that we have good title to all goods sold. WE GIVE NO WARRANTY, WHETHER OF MERCHANTABILITY, FITNESS FOR PURPOSE OR OTHERWISE, EXPRESS OR IMPLIED, OTHER THAN AS EXPRESSLY SET FORTH HEREIN. Users shall determine the suitability of the product for intended application before using.