

CAPPING CEMENT SPECIFICATION

Grade Name: P11/MO

Applications:

Grade for linear fluorescent lamps giving high torque strength and moisture resistance.

Physical appearance:

Powder appearance: Not applicable
Paste appearance: Dark green coloured paste
Cured appearance: Straw/yellow coloured expanded solid

Physical properties:

Solvent: ethanol (94%)
Powder:solvent ratio: not applicable L/100Kg powder @ 23°C
Viscosity: 345 - 355 (+/- 5) 10ths/mm paste penetration @ 23°C
Powder density: not applicable g/cm³ (tapped)
Paste density: 1.9 - 2.1 g/cm³
Average expansion: 70 - 90 %
Moisture resistance: very good
Paste storage life: 8 weeks Stored in sealed containers @ 21°C
(Note - Higher temperatures reduce life)
Powder storage life: not applicable

The above properties are given for guidance purposes only. Individual customer requirements should be assessed prior to the use of cement. Technical assistance and test methods are available on request.

Health and Safety data sheets are available upon request

The information contained on this specification sheet is given in good faith and does not constitute a warranty or guarantee for the customer. Customers are advised to ensure that all products are thoroughly tested to ensure suitability for the intended application.

Capping cement information

Recommended cleaning solvent: Ethanol, isopropanol

Recommended mixing sequence: Not applicable

Recommended mixing machines: Not applicable

<u>Recommended quantity of paste by cap type*:</u> (for guidance only)	T8	0.8 - 1.2 g
	T10	1.3 - 1.5 g
	T12	1.6 - 2.0 g

Curing Parameters: As cement curing is influenced by paste weight, curing temperature and time, precise figures cannot be given. For guidance purposes:

2 grams of paste @200°C will cure in 35 - 40 seconds
2 grams of paste @160°C will cure in 150 - 160 seconds

Prolonged exposure of curing cement to temperatures above 250°C should be avoided

The above properties are given for guidance purposes only. Individual customer requirements should be assessed prior to the use of cement. Technical assistance and test methods are available on request.

Health and Safety data sheets are available upon request

The information contained on this specification sheet is given in good faith and does not constitute a warranty or guarantee for the customer. Customers are advised to ensure that all products are thoroughly tested to ensure suitability for the intended application.

Glassbond (NW) Ltd, West Side Industrial Estate,
Jackson Street, St Helens, Merseyside, WA9 3AT, England
Tel: +44 (0) 1744 730 334 Fax: +44 (0) 1744 453 242
Website: www.glassbond.co.uk
Directors: ME Cordell Managing Director, PJ Randell, RJ Randell, DJ Randell (M.LM)
Glassbond (NW) Ltd. Registered office: West Side Industrial Estate
Registered in England No 1378679

