# SAFETY DATA SHEET



Safety Data Sheet according to regulation (EC) N°1907/2006, 1272/2008(CLP) & 453/2010

Date Revised : 11/07/2023 Revision : 05

Product : GLASSBOND SAUEREISEN TEMPSEAL CEMENT PASTE N°3 MOD 18

### SECTION 1: IDENTIFICATION OF THE SUBSTANCE/ MIXTURE AND OF THE COMPANY/UNDERTAKING

1.1 Product Identifier

Product name : Glassbond sauereisen Tempseal Cement Paste N°3 mod 18
REACH notes : Mixture- Substances contained in this product that are

not classified as hazardous have been/will be registered for

UK/EU REACH at the appropriate time.

1.2 Relevant identified uses of the mixture and uses advised against.

Identified use : Potting and encapsulation for electrical insulation

Uses advised against : No other uses

1.3 Details of the supplier of the safety data sheet

Company identification Glassbond (NW) Ltd

West Side Industrial Estate

Jackson Street St. Helens

Merseyside WA9 3AT United Kingdom

Telephone +44(0)1744730334Fax +44(0)1744451661

Email technical@glassbond.co.uk

**1.4** Emergency telephone +44(0)1744 730334

**number** (GMT, English spoken, Mon-Friday; 08.30-16.30)

# **SECTION 2: HAZARDS IDENTIFICATION\***

### 2.1 Classification of the mixture: calculation method

**2.1.1** Regulation (EC) No. 1272/2008(CLP)

Physical/Chemical NOT CLASSIFIED Human health NOT CLASSIFIED Environmental NOT CLASSIFIED

# 2.2 Label elements According to Regulation (EC) No. 1272/2008(CLP)

NONE

Print date

17/07/2023

Date Revised : 11/07/2023 Revision : 05

Product : Glassbond Sauereisen Tempseal Cement Paste N°3 mod 18

SIGNAL WORD (S) NONE

HAZARD NONE

STATEMENT(S)

PRECAUTIONARY STATEMENT(S)

### 2.3 Other Hazards

PBT: This mixture contains no substances considered as PBT vPvB: This mixture contains no substances considered as vPvB

**2.4 Additional** For full text of H/F information

For full text of H/P phrases see section 16 if not written out in full above.

# SECTION 3: COMPOSITION/INFORMATION ON INGREDIENTS\*

- **3.1** Substances (This product is a mixture according to EU legislation)
- **3.2** Mixture of none hazardous inorganic powders

Hazardous ingredient	% w/w	CAS Nº	EC N°	REACH N°	CPL EC 1272/2008
Lithium silicate	<10	12627-14-4	235-730-0	Pre-registered	H319: H315

#### 3.3 Additional information

For full text of H/P phrases see section 16 if not written out in full above.

Date Revised : 11/07/2023 Revision : 05

Product : Glassbond sauereisen Tempseal Cement Paste N°3 mod 18

#### **SECTION 4: FIRST AID MEASURES**

## 4.1 Description of first aid measures

General advice 
Immediately remove contaminated clothing, take care not to contaminate

unaffected areas.

Inhalation No emergency care anticipated, other than removal from exposure.

Eyes Rinse immediately with running water for at least 15 minutes holding the eyelid

open; consult an eye specialist.

Skin Wash thoroughly with water and soap

If skin irritation or rash occurs get medical attention (P333+P313)

Ingestion Immediately rinse the mouth with water and drink plenty of water. Obtain

medical attention immediately, show this safety data sheet.

#### 4.2 Most important symptoms and effects, both acute and delayed

Symptoms Eye contact- May cause temporary eye irritation.

Risks No information available

# 4.3 Indication of any immediate medical attention and special treatment needed

Treatment Treat according to symptoms (decontamination, vital functions), no known

specific antidote.

#### **SECTION 5: FIRE FIGHTING MEASURES**

# 5.1 Extinguishing media:

Suitable: CO2 or dry chemical spray, water spray may help to reduce the temperature and

extinguish flames for surrounding materials.

Unsuitable: High pressure water jet.

### 5.2 Special hazards arising from the mixture

The paste will not burn but the packaging is combustible.

### 5.3 Advice for fire fighters

Normal precautions are satisfactory.

**Further information**: The degree of risk is governed by the burning substance and the fire conditions. Contaminated extinguishing media must be disposed of in accordance with official regulation.

#### **SECTION 6: ACCIDENTAL RELEASE MEASURES**

# 6.1 Personal Precautions, protective equipment and emergency procedures

Use personal protective clothing.

# **6.2 Environmental Precautions**

Prevent contamination of soil, drains and surface waters. Do not discharge contaminated water/ fire-fighting water into drains/ surface water/ groundwater.

# 6.3 Methods and material for containment and cleaning up

Soak up with inert absorbent (e.g., sand). Collect spillage by scraping up. Dispose of material in accordance with official regulations.

#### 6.4 Reference to other sections

For personal protection see section 8 and disposal section 13

Date Revised : 11/07/2023 Revision : 05

Product : GLASSBOND SAUEREISEN TEMPSEAL CEMENT PASTE Nº3 MOD 18

#### **SECTION 7: HANDLING AND STORAGE**

# 7.1 Precautions for safe handling

Advice on safe handling For PPE see section 8. Contaminated clothing should not be

allowed out of the workplace (P272). Wash contaminated

clothing before reuse (P363)

Advice on protection Normal measures for preventive fire protection

against fire and explosion Take precautionary measures against static discharge

if using plastic packaging.

## 7.2 Conditions for safe storage, including any incompatibilities

Keep containers tightly closed. The paste should be stored under cover, in a well

ventilated, cool, dry place and away from direct sunlight or heat.

Protect from temperatures below: 4°C Protect from temperatures above: 35 °C

Suitable storage materials: Original containers.

Higher temperatures will reduce the shelf life of the product.

Under normal conditions (21°C) a shelf life of 3 months or more is possible.

### 7.3 Specific end use(s) As per section 1.2

#### **SECTION 8: EXPOSURE CONTROLS/PERSONAL PROTECTION**

# 8.1 Control parameters

# 8.1.1 Occupational Exposure Limits: OEL (Occupational Exposure Standard OES)

TWA STEL	mg/m <sup>3</sup>	ppm	(EH40 UK) OES 8 hr (EH40 UK)
TWA STEL			(EH40 UK) (EH40 UK)
TWA STEL			(EH40 UK) (EH40 UK)

8.1.2 Biological limit value Not available8.1.3 PNECs and DNELs Not available

#### 8.2 Exposure Controls

**8.2.1** Appropriate engineering controls: Effective exhaust ventilation system

# **8.2.2 Personal Protective Equipment:**

Eye/face Tightly fitting safety goggles (e.g., EN166)

Protection

Hand

Skin Protection/ Gloves: Chemical resistant gloves (e.g., EN374) Butyl rubber: 0.7 mm

coating thickness. Nitrile rubber: 0.4 mm coating thickness. Check with PPE

manufacturer. Replace immediately if signs of degradation are observed.

Other Wear closed work clothing.

Respiratory Should not be required under normal working conditions

Protection

Hygiene measures General industrial hygiene practice

# 8.2.3 Environmental exposure controls

No special environmental precautions required

Date Revised : 11/07/2023 Revision : 05

Product : GLASSBOND SAUEREISEN TEMPSEAL CEMENT PASTE N°3 MOD 18

#### **SECTION 9: PHYSICAL AND CHEMICAL PROPERTIES**

# 9.1 information on basic physical and chemical properties

APPEARANCE	Paste	COLOUR	White
Odour	None	ODOUR THRESHOLD ppm	Not Available
pH Value	9-11	RELATIVE DENSITY	2.5 g/ml
MELTING POINT/FREEZING PT	0°C	SOLUBILITY IN WATER @ 20°C	Partially soluble
INITIAL BOILING POINT/RANGE	100°C	PARTITION COEFFICIENT	Not available
FLASHPOINT °C	Not applicable	(n-octanol/water)	
EVAPORATION RATE	Not applicable	AUTO IGNITION TEMPERATURE	Not available
FLAMMABILITY (SOLID/GAS)	Not applicable	DECOMPOSITION TEMPERATURE °C	Not available
UPPER EXPLOSIVE LIMIT	Not Available	VISCOSITY mPa.s @ 20°C	17000-18000 cps
LOWER EXPLOSIVE LIMIT	Not Available	EXPLOSIVE PROPERTIES	Not available
VAPOUR PRESSURE	Not applicable	OXIDIZING PROPERTIES	Not oxidising
Vapour density (air=1)	Not applicable		

#### 9.2 Other information

#### **SECTION 10: STABILITY AND REACTIVITY**

10.1	Reactivity	Stable under normal conditions.
10.2	Chemical Stability	Stable under recommended storage and handling conditions.
10.3	Possibility of	No dangerous reaction known under conditions of normal use
	<b>Hazardous reactions</b>	
10.4	Conditions to Avoid	No decomposition if stored and applied as directed.
10.5	Incompatible	Acids. Reacts with aluminium, zinc and alloys of these metals
	materials	with liberation of hydrogen, which is flammable and forms an explosive mixture with air.
10.6	Hazardous	Hydrogen, by reaction with metals.
	Decomposition	
	Products	

#### **SECTION 11: TOXICOLOGICAL INFORMATION**

# 11.1 Information on toxicological effects of the mixture

o. . .

Acute toxicity

The poisonous effect of the product is caused by its basicity and not by substance-specific systemic characteristics. The LD50 value is of no practical significance due to the caustic effect of the product.

LD 50 ORAL TOXICITY RATS	mg/kg
LD <sub>50</sub> DERMAL TOXICITY RATS	ml/kg
LC 50 INHL TOXICITY IN RATS	mg/kg
LD 50 ORAL TOXICITY RATS	mg/kg
LD <sub>50</sub> DERMAL TOXICITY RABBITS	mg/kg
LC 50 INHL TOXICITY IN RATS	mg/kg

Skin corrosion/ irritation
Serious eye damage/ irritation
Respiratory or skin sensitisation
Germ cell mutagenicity
Carcinogenicity

Print date 17/07/2023

Contains component that may irritate skin Contains component that may irritate eyes

Not classified Not classified Not classified

: 11/07/2023 Date Revised Revision: 05

Product : GLASSBOND SAUEREISEN TEMPSEAL CEMENT PASTE N°3 MOD 18

Reproductive toxicity Not classified STOT SE (SINGLE exposure) Not classified STOT RE (REPEATED exposure) Not classified Aspiration hazard Not classified

#### 11.2 Other information

Health injuries are not known or expected under normal use.

#### **SECTION 12: ECOLOGICAL INFORMATION**

12.1 Toxicity		NOT AVAILABLE		
LL <sub>50</sub> Fish EC <sub>50</sub> Invertebrates EL <sub>50</sub> Algae	(96 hr) (48 hr) (72hr)	>100 Lithium silicate >800 Lithium silicate	mg/l mg/l mg/l	Brachydanio rerio Daphnia magna Selenastrum capricornutum
LL <sub>50</sub> Fish EC <sub>50</sub> Invertebrates EL <sub>50</sub> Algae	(96 hr) (48 hr) (72hr)		mg/l mg/l mg/l	Lepomis macrochirus Daphnia magna Selenastrum capricornutum

Microorganisms/ effect upon activated sludge

EC<sub>50</sub> Bacteria (3.0 hr)mg/l Activated sludge, domestic

#### 12.2 **Persistence and** degradability

Decomposition: not applicable, inorganic product.

#### 12.3 Not available Bioaccumulative potential

#### 12.4 By appropriate dumping into biological water treatment **Mobility**

plants no disruptive effect on the activity of activated

sludge is to be expected.

#### 12.5 Results of PBT and vPvB

assessment

PBT: This mixture contains no substances considered as

**PBT** 

vPvB: This mixture contains no substances considered

as vPvB

#### 12.6 Other adverse effects

When introducing acid or alkaline products into sewage disposal plants, the waste water must not be above or below a pH value of 6 to 10, for a displacement of the ph-value may cause disturbances in sewers and biological sewage works. Local rules have priority.

Date Revised : 11/07/2023 Revision : 05

Product : GLASSBOND SAUEREISEN TEMPSEAL CEMENT PASTE N°3 MOD 18

#### **SECTION 13: DISPOSAL CONSIDERATION**

#### 13.1 Waste treatment methods

The preparation must be disposed of by special means. Dispose by landfill via a licensed waste disposal contractor in accordance with local and national regulations.

Contaminated packaging should be emptied as far as possible, they can then be recycled after being thoroughly cleaned by a licensed contractor. Labels must not be removed from containers until they have been cleaned. Packaging materials that are not contaminated should be treated as household waste or as recycling material.

#### 13.2 Additional information

The UK Environmental Protection (Duty of Care) regulations (EP) and amendments should be noted (United Kingdom)

Dispose of contents/ container according to the end user disposal procedure (P501)

#### **SECTION 14: TRANSPORT INFORMATION**

#### **14.1 UN number** NOT CLASSIFIED

ADR

**RID** 

**IMDG** 

IATA

ADN

### **14.2 Proper shipping name** NOT CLASSIFIED

ADR

**RID** 

**IMDG** 

**IATA** 

ADN

# 14.3 Transport Hazard Class NOT CLASSIFIED

ADR

RID

**IMDG** 

IATA

ADN

# 14.4 Packing Group NOT CLASSIFIED

ADR

**RID** 

**IMDG** 

IATA

ADN

# 14.5 Environmental hazards NOT CLASSIFIED

ADR

RID

**IMDG** 

IATA

ADN

#### 14.6 Special Precautions for user

Always transport in closed containers that are upright and secure. Ensure that persons transporting the product know what to do in the event of accident or spillage

Date Revised : 11/07/2023 Revision : 05

Product : GLASSBOND SAUEREISEN TEMPSEAL CEMENT PASTE N°3 MOD 18

# 14.7 Transport in bulk according to Annex II of MARPOL 73/78 and the IBC code

Not applicable

#### **SECTION 15: REGULATORY INFORMATION**

# 15.1 Safety, health and environmental regulations/legislation specific for the mixture

**EU** Legislation

Commission Regulation (EC) No 474/2014 of 8<sup>th</sup> May 2014 amending Annex XVII to Regulation (EC) No 1907/2006

Commission Regulation (EC) No 944/2013 of 2<sup>nd</sup> October 2013 (5<sup>th</sup> ATP) amending Regulation (EC) No 1272/2008 on classification, labelling and packaging of substances and mixtures.

Waste Framework Directive 2008/98/EC

Employment restrictions: Observe employment restrictions for young people, for child bearing mothers/ nursing and for women of child-bearing age.

# 15.2 Chemical Safety Assessment

Exposure scenarios are not required for this mixture because it is not classified as dangerous according to Directive 67/548/EEC and assessed to be not PBT/vPvB. No risk management measures as defined by REACH have been identified.

### SECTION 16: OTHER INFORMATION \*

\* SECTIONS REVISED 2 Supersedes date 04/02/2022

Removal of section 2.1.2

Legend

PBT Persistent, Bioaccumulative and Toxic VPVB very Persistent and very Bioaccumulative

Data sources Supplier information

Other hazard phrases listed in this MSDS

H319 Causes serious Eye Irritation Cat 2
H315 Causes skin irritation Skin Irr 2

Training advice General industrial hygiene practice.

Manual handling

Further information

Print date

17/07/2023

This information relates only to the specific material designated and is to the best of the company's knowledge and belief, accurate and reliable as of the date indicated. However, no warranty guarantee or representation is made to its accuracy, reliability or completeness and without acceptance of liability for loss or damage attributable to reliance thereon as conditions of use lie outside our control. Users should always carry tests to establish the suitability of any products for their intended applications. No statements shall be incorporated in any contract unless expressively agreed in writing or construed as recommending the use of any product in conflict of any patent. All goods are supplied subject to Glassbond Ltd's General Conditions of Sale.